



# MegaFlow SP403

High Performance Superplasticiser with Superior Slump Retention Properties

**DESCRIPTION** **MegaFlow SP403** is a superior grade naphthalene based superplasticiser designed for high performance concrete mixes in extreme weather conditions.

**STANDARD** ASTM C494, Type B, D and G, BSEN 934-2

**USES** **MegaFlow SP403** is specially recommended for concrete designed with durability criteria, containing GGBS, micro silica, fly ash, etc. and low water to binder ratios. It is used for pumpable concrete with greater time duration of slump retention requirements. It is extremely useful in concretes for piling, congested reinforcement, high rise towers, and mass concrete with temperature control for raft foundations, etc.

**ADVANTAGES**

- Very high water reduction capability
- High grade concrete without excessive cement content
- Superior slump retention even in hot climates without set retardation
- Controlled hydration for temperature monitored concrete
- Increases durability by reducing permeability
- Better pumpability
- Chloride free and safe for use in prestressed and reinforced concrete

## TYPICAL PROPERTIES at 25°C

PROPERTY	TEST METHOD	VALUE
Component	-	Single
Form	-	Liquid
Colour	-	Brown
Specific Gravity	ASTM C494	1.22 +/- 0.02
Air Entrainment	ASTM C231	Up to 1% over control mix
Chloride Content	BSEN 480-10	Nil to BSEN 934-2
pH	ASTM C494	7-9

**COMPATIBILITY** **MegaFlow SP403** can be used with all types of cements and cementitious materials like fly ash, GGBS, microsilica, etc. It should not be premixed with other admixtures.

**DOSAGE** Recommended dosage is 0.5 - 3% by weight of cementitious material. Higher dosage can be used after verification by conducting lab and site trials. Optimum dosage of **MegaFlow SP403** and effect on concrete properties such as workability, strength, setting time, etc. are best assessed after preliminary tests on site using the actual materials of mixes under consideration.

**EFFECT OF OVERDOSING** Overdosing may result in higher workability and delay in setting. If intentionally or accidentally increased above the recommended limit, ensure that the stripping time of



## MegaFlow SP403

formwork is extended accordingly. In such cases, however, provided the concrete is properly cured, the ultimate strength will generally be higher than the regular concrete. The effect of overdosing are increased when sulphate resistance cement is used in the concrete mixes, because of the chemical nature of the cement as compared to that of OPC.

<b>PACK SIZE</b>	20 ltr, 200 ltr, 1000 ltr and bulk	
<b>DISPENSING</b>	<b>MegaFlow SP403</b> should be directly dispensed into the concrete mixer together with the mixing water.	
<b>GENERAL INFORMATION</b>	<b>Shelf Life</b>	12 months from date of manufacture when stored under warehouse conditions in original unopened packing. Extreme temperature / humidity may reduce shelf life.
	<b>Cleaning</b>	Clean all equipment and tools with water immediately after use.
<b>HEALTH and SAFETY</b>	<b>PPE's</b>	Gloves, goggles and suitable mask must be worn.
	<b>Precautions</b>	Contact with skin, eyes etc. must be avoided. If swallowed seek medical attention immediately.
	<b>Hazard</b>	Regarded as non-hazardous for transportation.
	<b>Disposal</b>	Do not reuse containers. To be disposed off as per local rules and regulations.
	<b>Additional Information</b>	Refer MSDS. (Available on request)
<b>TECHNICAL SERVICE</b>	<b>CONMIX Technical Services</b> are available on request for onsite support to assist in the correct use of its products.	



Construction Solutions for Africa

### CAPE TOWN

Tel: +27 (0)87 231 0253  
Unit 5 | M5 Freeway Park  
Upper Camp Rd | Maitland | 7405  
Cape Town | South Africa

### JOHANNESBURG

Tel: +27 (0)82 785 8529  
64 Maple Street | Pomona  
Kempton Park | Johannesburg | 1619  
South Africa

Email: [info@msasa.co.za](mailto:info@msasa.co.za) | [www.msasa.co.za](http://www.msasa.co.za)

Manufacturer:

### CONMIX LTD.

P.O. Box 5936, Sharjah  
United Arab Emirates  
Tel: +971 6 5314155  
Fax: +971 6 5314332  
Email: [conmix@conmix.com](mailto:conmix@conmix.com)

Sales Office:  
Tel: +971 6 5682422  
Fax: +971 6 5681442  
[www.conmix.com](http://www.conmix.com)



It is the customer's responsibility to satisfy themselves by checking with the company whether information is still current at the time of use. The customer must be satisfied that the product is suitable for the use intended. All products comply with the properties shown on current data sheets. However, Conmix does not warrant or guarantee the installation of the products as it does not have any control over installation or end use of the product. All information and particularly the recommendations relating to application and end use are given in good faith. The products are guaranteed against any manufacturing defects and are sold subject to Conmix standard terms and conditions of sale.